

Prosperity Dielectrics Co., Ltd.

No.566-1, Kaoshi Rd., Yangmei, Taoyuan 32668, Taiwan (R.O.C.)

Tel : 886-3-4753355

Fax : 886-3-4854959

Messrs. : 一般共用

Date : 2019/11/11

APPROVAL SHEET

Product Name : High Reliability Multilayer Ceramic Chip Capacitors

Part No. : FR Series

Description : Size 0603~2225, C0G/X7R, 25Vdc to 4000Vdc

PREPARED BY	APPROVED BY

信昌電子陶瓷股份有限公司

PROSPERITY DIELECTRICS CO., LTD.

桃園市楊梅區高獅路 566-1 號 <http://www.pdc.com.tw>

Tel : 03-4753355 ext :

Fax : 03-4854959

Contactor : _____ **Mobile :** _____

Prosperity Dielectrics Co., Ltd.

No.566-1, Kaoshi Rd., Yangmei, Taoyuan 32668, Taiwan (R.O.C.)

Tel : 886-3-4753355

Fax : 886-3-4854959

SPECIFICATION

FOR

Product Name : High Reliability Multilayer Ceramic Chip Capacitors

Part No. : FR Series

Description : Size 0603~2225, C0G/X7R, 25Vdc to 400Vdc

SPEC. No. : FR-000-001-07

DATE : 2019/11/11

DRAWN BY	CHECEKED BY	APPROVED BY
<i>Jane Hsiao</i>	<i>Yvens Chou</i>	<i>Joseph Ling</i>

1. INTRODUCTION

MLCC consists of a conducting material and electrodes. To manufacture a chip-type SMT and achieve miniaturization, high density and high efficiency, ceramic condensers are used.

PDC high capacitance MLCC offers low ESR and excellent frequency characteristics to be suited for coupling and decoupling applications in circuit. The high dielectric constant materials X7R are used for this series product.

2. FEATURES

- a. Realize high capacitance in small size.
- b. Capacitor with lead-free termination (pure Tin).
- c. RoHS compliant.
- d. HALOGEN compliant.
- e. Surface mount suited for wave and reflow soldering.
- f. High reliability and no polarity.
- g. Excellent in high frequency characteristic.

3. APPLICATIONS

- a. Digital circuit coupling or decoupling applications.
- b. For high frequency and high-density type power suppliers.
- c. For bypassing.
- d. Ideal for smoothing circuits.
- e. DC to DC converter.

4. HOW TO ORDER

<u>FR</u>	<u>31</u>	<u>X</u>	<u>471</u>	<u>K</u>	<u>251</u>	<u>P</u>	<u>X</u>	<u>G</u>
PDC Family	Size	Dielectric	Capacitance	Tolerance	Rated Voltage	Packaging	Thickness	Control Code
Table 1	Table 2	Table 3	Table 4	Table 5	Table 6	Table 7	Table 8	Table 9

Table 1	PDC Family	
Code	Description	
FR	High Quality Equipment Capacitor	

Table 2	Size					
Code	Description	Code	Description	Code	Description	
15	0402 (1005)	32	1210 (3225)	52	2211 (5728)	
18	0603 (1608)	42	1808 (4520)	55	2220 (5750)	
21	0805 (2012)	43	1812 (4532)	56	2225 (5763)	
31	1206 (3216)	46	1825 (4563)			

Table 3	Dielectric Material Characteristics			
Code	Description	Code	Description	
N	COG	X	X7R	
B	X5R	F	Y5V	

Table 4	Capacitance Rule Code			
Code	Description	Code	Description	
R47	0.47pF	102	102=10x10 ² =1000pF	
0R5	0.5pF	104	104=10x10 ⁴ =100nF	
100	100=10x10 ⁰ =10pF	106	106=10x10 ⁶ =10μF	

Table 5	Tolerance					
Code	Description	Code	Description	Code	Description	
A	±0.05 pF	J	±5 %	X	+10% ~ +20%	
B	±0.10 pF	K	±10 %			
C	±0.25 pF	L	0% ~ +10%			
D	±0.50 pF	M	±20 %			
F	±1 %	N	-5% ~ +10%			
G	±2 %	P	±0.02 pF			
H	±3 %	Q	±0.03 pF			
I	-10% ~ 0%	Z	-20% ~ +80%			

Table 6	Rated Voltage					
Code	Description	Code	Description	Code	Description	
6R3	6.3VDC	201	200VDC	152	1500VDC	
100	10VDC	251	250VDC	202	2000VDC	
160	16VDC	401	400VDC	302	3000VDC	
250	25VDC	501	500VDC	402	4000VDC	
500	50VDC	631	630VDC	502	5000VDC	
101	100VDC	102	1000VDC	602	6000VDC	

Table 7	Packaging Type			
Code	Description	Code	Description	
B	Bulk	T	Tray package	
E	Tape and 7" Reel, Embossed Tape	P	Tape and 7" Reel, Paper Tape	
K	Tape and 10" Reel, Embossed Tape	D	Tape and 10" Reel, Paper Tape	
L	Tape and 13" Reel, Embossed Tape	G	Tape and 13" Reel, Paper Tape	

Table 8	Thickness Description					
Code	Description	Code	Description	Code	Description	
A	0.60 ± 0.10 mm	I	1.25 ± 0.20 mm	Q	0.50 +0.02/-0.05 mm	
B	0.8 +0.15/-0.10 mm	J	1.15 ± 0.15 mm	R	3.10 ± 0.30 mm	
C	1.25 ± 0.10 mm	K	0.50 ± 0.20 mm	S	0.80 ± 0.07 mm	
D	1.40 ± 0.15 mm	L	0.30 ± 0.03 mm	T	0.85 ± 0.10 mm	
E	1.60 ± 0.20 mm	M	0.95 ± 0.10 mm	U	0.50 ± 0.10 mm	
F	2.00 ± 0.20 mm	N	0.50 ± 0.05 mm	V	0.20 ± 0.02 mm	
G	2.50 ± 0.30 mm	O	3.50 ± 0.20 mm	X	0.80 ± 0.10 mm	
H	2.80 ± 0.30 mm	P	1.60 +0.3/-0.10 mm	Z	0.25 ± 0.03 mm	

Table 9	Special Control Code	
Code	Description	
G	RoHS Compliant	
Q	Surface Coating (size 1206~2225)	

Prosperity Dielectrics Co., Ltd.

5. EXTERNAL DIMENSIONS


Size Inch (mm)	L (mm)	W (mm)	Code / T (mm)	M _B (mm)	
0603(1608)	1.60±0.15	0.80±0.15	See No.4 Reference Table 8	0.40±0.15	
0805(2012)	2.00±0.20 2.10±0.20*	1.25±0.20		0.50±0.20	
1206(3216)	3.20±0.20 3.30±0.30*	1.60±0.20		0.60±0.20	
1210(3225)	3.20±0.30 3.30±0.40*	2.50±0.30		0.75±0.35	
1808(4520)	4.50±0.40 4.50 +0.50/-0.30*	2.00±0.25		0.75±0.35	
1812(4532)	4.50±0.40 4.50 +0.50/-0.30*	3.20±0.30 3.20±0.40*		0.75±0.35	
1825(4563)	4.50±0.40 4.50 +0.50/-0.30*	6.30±0.40		0.75±0.35	
2220(5750)	5.70±0.40	5.00±0.40		0.85±0.35	
2225(5763)	5.70±0.40	6.30±0.40		0.85±0.35	

Fig. 5.1 The outline of MLCC

** Means rated voltage ≥ 1000Vdc

6. GENERAL ELECTRICAL DATA

Dielectric	C0G	X7R
Size	0603, 0805, 1206, 1210, 1808, 1812, 1825, 2220, 2225	
Rated voltage (WVDC)	25V, 50V, 100V, 200V, 250V, 500V, 630V, 1000V, 1500V, 2000V, 3000V, 4000V	
Capacitance range*	0.5pF ~ 330nF	100pF ~ 22μF
Capacitance tolerance	Reference to Table 5	
Tan δ	Cap. Rang	Q Spec.
	Cap.<30pF	Q≥400+20C
	Cap.≥30pF	Q≥1000
Capacitance & Tan δ Test condition	Measured at the condition of 30~70% related humidity	
	For 25°C at ambient temperature	Preconditioning for Class II MLCC : Perform a heat treatment at 150±10°C for 1 hour, then leave in ambient condition for 24±2 hours before measurement
	Cap. Rang	Test Condition
	Cap.≤1000pF	1.0±0.2Vrms, 1.0MHz±10%
Cap.>1000pF	1.0±0.2Vrms, 1.0kHz±10%	1.0±0.2Vrms, 1.0KHz±10% for Cap.≤10μF and 0.5±0.2Vrms, 120Hz±20% for Cap.>10μF, at 25°C ambient temperature
Insulation resistance at Ur	≥100GΩ or RxC≥500Ω-F, whichever is smaller	≥10GΩ or RxC≥100Ω-F, whichever is smaller
Operating temperature	-55°C to +125°C	
Capacitance characteristic	±30ppm/°C	±15%
Termination	Cu or Ag/Ni/Sn or Au (lead-free termination)	

7. CAPACITANCE RANGE

7-1. C0G

Dimension		0603					0805							
Cap. (pF)	Code	25V	50V	100V	200V	250V	25V	50V	100V	200V	250V	500V	630V	1000V
0.5	0R5	S	S	S	S	S	A	A	A	A	A	A	A	
0.6	0R6	S	S	S	S	S	A	A	A	A	A	A	A	
0.7	0R7	S	S	S	S	S	A	A	A	A	A	A	A	
0.8	0R8	S	S	S	S	S	A	A	A	A	A	A	A	
0.9	0R9	S	S	S	S	S	A	A	A	A	A	A	A	
1.0	1R0	S	S	S	S	S	A	A	A	A	A	A	A	
1.2	1R2	S	S	S	S	S	A	A	A	A	A	A	A	
1.5	1R5	S	S	S	S	S	A	A	A	A	A	A	A	C
1.8	1R8	S	S	S	S	S	A	A	A	A	A	A	A	C
2.2	2R2	S	S	S	S	S	A	A	A	A	A	A	A	C
2.7	2R7	S	S	S	S	S	A	A	A	A	A	A	A	C
3.3	3R3	S	S	S	S	S	A	A	A	A	A	A	A	C
3.9	3R9	S	S	S	S	S	A	A	A	A	A	A	A	C
4.7	4R7	S	S	S	S	S	A	A	A	A	A	A	A	C
5.0	5R0	S	S	S	S	S	A	A	A	A	A	A	A	C
5.6	5R6	S	S	S	S	S	A	A	A	A	A	A	A	C
6.8	6R8	S	S	S	S	S	A	A	A	A	A	A	A	C
8.2	8R2	S	S	S	S	S	A	A	A	A	A	A	A	C
10	100	S	S	S	S	S	A	A	A	A	A	A	A	C
12	120	S	S	S	S	S	A	A	A	A	A	A	A	C
15	150	S	S	S	S	S	A	A	A	A	A	A	A	C
18	180	S	S	S	S	S	A	A	A	A	A	A	A	C
22	220	S	S	S	S	S	A	A	A	A	A	A	A	C
27	270	S	S	S	S	S	A	A	A	A	A	A	A	C
33	330	S	S	S	S	S	A	A	A	A	A	A	A	C
39	390	S	S	S	S	S	A	A	A	A	A	A	A	C
47	470	S	S	S	S	S	A	A	A	A	A	A	A	C
56	560	S	S	S	S	S	A	A	A	A	A	A	A	C
68	680	S	S	S	S	S	A	A	A	A	A	A	A	C
82	820	S	S	S	S	S	A	A	A	A	A	X	X	C
100	101	S	S	S	S	S	A	A	A	A	X	X	X	C
120	121	S	S	S	S	S	A	A	A	A	X	C	C	C
150	151	S	S	S	S	S	A	A	A	X	X	C	C	C
180	181	S	S	S	S	S	A	A	A	X	C	C	C	C
220	221	S	S	S	S	S	A	A	A	C	C	C	C	C
270	271	S	S	S	B	B	A	A	A	C	C	C	C	C
330	331	S	S	S	B	B	A	A	A	C	C	C	C	
390	391	S	S	S	B	B	X	X	X	C	C	C	C	
470	471	S	S	S	B	B	X	X	X	C	C	C	C	
560	561	S	S	S	B	B	X	X	X	C	C	C	C	
680	681						X	X	X	C	C	C	C	
820	821						X	X	X	C	C	C	C	
1000	102						X	X	X	C	C	C	C	
1200	122						X	X	X	C	C			
1500	152						X	X	X	C	C			
1800	182						X	X	X	C	C			
2200	222						X	X	X	C	C			
2700	272						C	C	C	C	C			
3300	332						C	C	C					
3900	392						C	C	C					
4700	472						C	C	C					
5600	562						C	C						
6800	682													
8200	822													
10000	103													

7. CAPACITANCE RANGE

7-1. C0G

Dimension		1206										1210											
Cap.(pF)	Code	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V
1.2	1R2	X	X	X																			
1.5	1R5	X	X	X	X	X	X	X	X	X	X												
1.8	1R8	X	X	X	X	X	X	X	X	X	X												
2.2	2R2	X	X	X	X	X	X	X	X	X	X												
2.7	2R7	X	X	X	X	X	X	X	X	X	X												
3.3	3R3	X	X	X	X	X	X	X	X	X	X												
3.9	3R9	X	X	X	X	X	X	X	X	X	X												
4.7	4R7	X	X	X	X	X	X	X	X	X	X												
5.0	5R0	X	X	X	X	X	X	X	X	X	X												
5.6	5R6	X	X	X	X	X	X	X	X	X	X												
6.8	6R8	X	X	X	X	X	X	X	X	X	X												
8.2	8R2	X	X	X	X	X	X	X	X	X	X												
10	100	X	X	X	X	X	X	X	X	X	X	E	M	M	M	M	M	M	M	M	M	M	F
12	120	X	X	X	X	X	X	X	X	X	X	E	M	M	M	M	M	M	M	M	M	M	F
15	150	X	X	X	X	X	X	X	X	X	X	E	M	M	M	M	M	M	M	M	M	M	F
18	180	X	X	X	X	X	X	X	X	X	X	E	M	M	M	M	M	M	M	M	M	M	F
22	220	X	X	X	X	X	X	X	X	X	X	E	M	M	M	M	M	M	M	M	M	M	F
27	270	X	X	X	X	X	X	X	X	X	X	E	M	M	M	M	M	M	M	M	M	M	F
33	330	X	X	X	X	X	X	X	X	M	M	E	M	M	M	M	M	M	M	M	M	M	F
39	390	X	X	X	X	X	X	X	X	M	M	E	M	M	M	M	M	M	M	M	M	M	F
47	470	X	X	X	X	X	X	X	M	M	M	E	M	M	M	M	M	M	M	M	M	M	F
56	560	X	X	X	X	X	X	X	M	C	C	E	M	M	M	M	M	M	M	M	C	C	F
68	680	X	X	X	X	X	X	X	M	C	C	E	M	M	M	M	M	M	M	M	C	C	F
82	820	X	X	X	X	X	X	X	C	C	C	E	M	M	M	M	M	M	M	M	C	C	F
100	101	X	X	X	X	X	X	X	C	C	C		M	M	M	M	M	M	M	C	C	C	F
120	121	X	X	X	X	X	X	X	C	E	E		M	M	M	M	M	M	M	C	C	C	F
150	151	X	X	X	X	X	X	X	C	E	E		M	M	M	M	M	M	M	C	E	E	F
180	181	X	X	X	X	X	X	X	E	E	E		M	M	M	M	M	M	M	C	E	E	F
220	221	X	X	X	X	X	X	X	E	E	E		M	M	M	M	M	M	M	E	E	E	F
270	271	X	X	X	X	M	M	M	E	E	E		M	M	M	M	M	M	M	E	E	E	G
330	331	X	X	X	X	M	M	M	E	E	E		M	M	M	M	M	M	M	E	E	E	
390	391	X	X	X	X	M	M	M	E				M	M	M	M	M	M	M	E	E	E	
470	471	X	X	X	M	M	M	M	E				M	M	M	M	M	M	M	E	E	E	
560	561	X	X	X	M	C	C	C	E				M	M	M	M	M	M	M	E	E	E	
680	681	X	X	X	M	C	C	C	E				M	M	M	M	M	M	M	E	E	E	
820	821	X	X	X	M	E	E	E	E				M	M	M	M	M	M	M	E	E	E	
1000	102	X	X	X	M	E	E	E	E				M	M	M	C	C	C	C	E	F	F	
1200	122	X	X	X	M	E	E	E					M	M	M	C	C	C	C	E	F	F	
1500	152	X	X	X	C	E	E	E					M	M	M	C	C	C	C	F	G	G	
1800	182	X	X	X	C	E	E	E					M	M	M	C	C	C	C	G	G	G	
2200	222	X	X	X	C	E	E	E					M	M	M	C	C	C	C	G			
2700	272	X	X	X	C	E	E	E					M	M	M	C	C	C	C				
3300	332	X	X	X	C	E	E	E					M	M	M	C	C	C	C				
3900	392	X	X	X	E	E	E	E					M	M	M	C	C	C	C				
4700	472	X	X	X	E	E	E	E					M	C	C	C	C	C	C				
5600	562	X	X	X	E	E	E						M	C	C	C	C	C	C				
6800	682	M	M	M	E	E							M	E	E	E	E	E	E				
8200	822	C	C	C	E	E							M	E	E	E	E	E	E				
10000	103	C	C	C	E	E							M	E	E	F	F	F	F				
12000	123	P	P										C	E	E								
15000	153	P	P										C	E	F								
18000	183	P	P										F	F	G								
22000	223												F	F	G								
27000	273												F	G									
33000	333												F	G									
39000	393												G	G									
47000	473																						
56000	563																						
68000	683																						

7. CAPACITANCE RANGE

7-1. C0G

Dimension		1808												
Cap.(pF)	Code	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V	4000V	
2.2	2R2	C	C	C	C	C	C	C	C	C	C	C	C	
2.7	2R7	C	C	C	C	C	C	C	C	C	C	C	C	
3.3	3R3	C	C	C	C	C	C	C	C	C	C	C	C	
3.9	3R9	C	C	C	C	C	C	C	C	C	C	C	C	
4.7	4R7	C	C	C	C	C	C	C	C	C	C	C	C	
5.0	5R0	C	C	C	C	C	C	C	C	C	C	C	C	
5.6	5R6	C	C	C	C	C	C	C	C	C	C	C	C	
6.8	6R8	C	C	C	C	C	C	C	C	C	C	C	C	
8.2	8R2	C	C	C	C	C	C	C	C	C	C	C	C	
10	100	C	C	C	C	C	C	C	C	C	C	C	C	
12	120	C	C	C	C	C	C	C	C	C	C	C	C	
15	150	C	C	C	C	C	C	C	C	C	C	C	C	
18	180	C	C	C	C	C	C	C	C	C	C	C	C	
22	220	C	C	C	C	C	C	C	C	C	C	C	E	
27	270	C	C	C	C	C	C	C	C	C	C	C	E	
33	330	C	C	C	C	C	C	C	C	C	C	C	F	
39	390	C	C	C	C	C	C	C	C	C	C	C	F	
47	470	C	C	C	C	C	C	C	C	C	C	C		
56	560	C	C	C	C	C	C	C	C	C	C	C		
68	680	C	C	C	C	C	C	C	C	C	C	C		
82	820	C	C	C	C	C	C	C	C	C	C	C		
100	101	C	C	C	C	C	C	C	C	C	C	C	F	
120	121	C	C	C	C	C	C	C	C	C	C	C	F	
150	151	C	C	C	C	C	C	C	C	F	F	F		
180	181	C	C	C	C	C	C	C	C	F	F	F		
220	221	C	C	C	C	C	C	C	C	F	F	F		
270	271	C	C	C	C	C	F	F	F	F	F	F		
330	331	C	C	C	C	C	F	F	F	F	F	F		
390	391	C	C	C	C	C	F	F	F	F	F	F		
470	471	C	C	C	C	C	F	F	F	F	F	F		
560	561	C	C	C	C	C	F	F	F	F	F	F		
680	681	C	C	C	C	C	F	F	F	F	F	F		
820	821	C	C	C	C	C	F	F	F	F	F	F		
1000	102	C	C	C	C	C	F	F	F	F	F	F		
1200	122	C	C	C	C	C	F	F	F					
1500	152	C	C	C	C	C	F	F	F					
1800	182	C	C	C	C	C	F	F	F					
2200	222	C	C	C	C	C	F	F	F					
2700	272	C	C	C	C	C	F	F	F					
3300	332	C	C	C	C	C	F	F						
3900	392	C	C	C	C	C	F	F						
4700	472	C	C	C	C	C	F	F						
5600	562	C	C	C	E	E	F	F						
6800	682	C	C	C	E	E								
8200	822	C	C	E	F	F								
10000	103	C	C	E	F	F								
12000	123	E	E	F										
15000	153	E	E											
18000	183	F	F											
22000	223	F	F											
27000	273													
33000	333													
39000	393													
47000	473													
56000	563													
68000	683													
82000	823													
100000	104													
120000	124													
150000	154													

7. CAPACITANCE RANGE(Con.)

7-1. C0G

Dimension		1812											
Cap.(pF)	Code	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V	4000V
2.2	2R2												
2.7	2R7												
3.3	3R3												
3.9	3R9												
4.7	4R7												
5.0	5R0												
5.6	5R6												
6.8	6R8												
8.2	8R2												
10	100	C	C	C	C	C	C	C	C	C	C	C	C
12	120	C	C	C	C	C	C	C	C	C	C	C	C
15	150	C	C	C	C	C	C	C	C	C	C	C	C
18	180	C	C	C	C	C	C	C	C	C	C	C	C
22	220	C	C	C	C	C	C	C	C	C	C	C	C
27	270	C	C	C	C	C	C	C	C	C	C	C	C
33	330	C	C	C	C	C	C	C	C	C	C	C	
39	390	C	C	C	C	C	C	C	C	C	C	C	
47	470	C	C	C	C	C	C	C	C	C	C	C	
56	560	C	C	C	C	C	C	C	C	C	C	C	
68	680	C	C	C	C	C	C	C	C	C	C	C	
82	820	C	C	C	C	C	C	C	C	C	C	C	
100	101	C	C	C	C	C	C	C	C	C	C	C	
120	121	C	C	C	C	C	C	C	C	C	C	C	
150	151	C	C	C	C	C	C	C	C	C	C	C	
180	181	C	C	C	C	C	C	C	C	C	C	C	F
220	221	C	C	C	C	C	C	C	C	C	C	C	F
270	271	C	C	C	C	C	C	C	C	F	F	F	F
330	331	C	C	C	C	C	C	C	C	F	F	F	F
390	391	C	C	C	C	C	C	C	C	F	F	F	F
470	471	C	C	C	C	C	C	C	F	F	F	F	F
560	561	C	C	C	C	C	C	C	F	F	F	F	F
680	681	C	C	C	C	C	C	C	F	F	F	F	F
820	821	C	C	C	C	C	C	C	F	F	F	F	G
1000	102	C	C	C	C	C	C	C	F	F	F	F	G
1200	122	C	C	C	C	C	C	C	F	F	F	F	
1500	152	C	C	C	C	C	C	C	F	F	F	F	
1800	182	C	C	C	C	C	C	C	F	F	F	F	
2200	222	C	C	C	C	C	C	C	F	F	F	F	
2700	272	C	C	C	C	C	C	C	F	G	G	G	
3300	332	C	C	C	C	C	C	C	G	F	G	G	
3900	392	C	C	C	C	C	C	C	G				
4700	472	C	C	C	C	C	C	C	G				
5600	562	C	C	C	C	C	C	C					
6800	682	C	C	C	C	C	C	C					
8200	822	C	C	C	C	C	C	C					
10000	103	C	C	C	C	C	C	C					
12000	123	C	C	C	E	E	E	E					
15000	153	C	C	C	E	E	E	E					
18000	183	C	C	E	F	F	F	F					
22000	223	C	C	E	F	F	F	F					
27000	273	C	C	F	G	G							
33000	333	C	C	F									
39000	393	F	F	G									
47000	473	F	F	G									
56000	563	G	G										
68000	683	G	G										
82000	823	G	G										
100000	104	G	G										
120000	124												
150000	154												

Prosperity Dielectrics Co., Ltd.

7. CAPACITANCE RANGE(Con.)

7-1. C0G

Dimension		1825											2220											
Cap.(pF)	Code	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V	4000V
10	100	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
12	120	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
15	150	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
18	180	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
22	220	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
27	270	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
33	330	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
39	390	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
47	470	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
56	560	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
68	680	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
82	820	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
100	101	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
120	121	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
150	151	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
180	181	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
220	221	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
270	271	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	G
330	331	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	G	G
390	391	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	G	
470	471	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	G	
560	561	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	G	
680	681	F	F	F	F	F	F	F	F	F	F	G	F	F	F	F	F	F	F	F	F	F	G	
820	821	F	F	F	F	F	F	F	F	F	G	F	F	F	F	F	F	F	F	F	F	F	G	
1000	102	F	F	F	F	F	F	F	F	F	G	F	F	F	F	F	F	F	F	F	F	F	G	
1200	122	F	F	F	F	F	F	F	F	F	G	F	F	F	F	F	F	F	G	G	G	G	G	
1500	152	F	F	F	F	F	F	F	F	G	G	G	F	F	F	F	F	F	G	G	G	G	G	
1800	182	F	F	F	F	F	F	F	F	G	G	G	F	F	F	F	F	F	G	G	G	G		
2200	222	F	F	F	F	F	F	F	F	G	G		F	F	F	F	F	F	G	G	G			
2700	272	F	F	F	F	F	F	F	G	G			F	F	F	F	F	F	G	G	G			
3300	332	F	F	F	F	F	F	F	G	G			F	F	F	F	F	F	G	G	G			
3900	392	F	F	F	F	F	F	F	G	G			F	F	F	F	F	F	G	G	G			
4700	472	F	F	F	F	F	F	F	G	G			F	F	F	F	F	F	G	G	G			
5600	562	F	F	F	F	F	F	F	G				F	F	F	F	F	F	G					
6800	682	F	F	F	F	F	F	F	G				F	F	F	F	F	F	G					
8200	822	F	F	F	F	F	F	F	G				F	F	F	F	F	F	G					
10000	103	F	F	F	F	F	F	F	G				F	F	F	F	F	F	G					
12000	123	F	F	F	F	F	F	F					F	F	F	F	F	F						
15000	153	F	F	F	F	F	F	F					F	F	F	F	F	F						
18000	183	F	F	F	F	F	F	F					F	F	F	F	F	F						
22000	223	F	F	F	F	F	F	F					F	F	F	F	F	F						
27000	273	F	F	F	F	F	F	F					F	F	F	F	F	F						
33000	333	F	F	F	F	F	F	F					F	F	F	F	F	F						
39000	393	F	F	F	F	F	G						F	F	F	F	F	G						
47000	473	F	F	F	F	F	G						F	F	F	G	G	G						
56000	563	F	F	F	G	G	G						F	F	F	G	G							
68000	683	F	F	F	G	G							F	F	F	G	G							
82000	823	F	F	G									G	G	G									
100000	104	G	G	G									G	G	G									
120000	124																							
150000	154																							
180000	184																							
220000	224																							
270000	274																							

Prosperity Dielectrics Co., Ltd.

7. CAPACITANCE RANGE(Con.)

7-1. C0G

Dimension		2225											
Cap.(pF)	Code	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V	4000V
10	100	F	F	F	F	F	F	F	F	F	F	F	
12	120	F	F	F	F	F	F	F	F	F	F	F	
15	150	F	F	F	F	F	F	F	F	F	F	F	
18	180	F	F	F	F	F	F	F	F	F	F	F	
22	220	F	F	F	F	F	F	F	F	F	F	F	
27	270	F	F	F	F	F	F	F	F	F	F	F	F
33	330	F	F	F	F	F	F	F	F	F	F	F	F
39	390	F	F	F	F	F	F	F	F	F	F	F	F
47	470	F	F	F	F	F	F	F	F	F	F	F	F
56	560	F	F	F	F	F	F	F	F	F	F	F	F
68	680	F	F	F	F	F	F	F	F	F	F	F	F
82	820	F	F	F	F	F	F	F	F	F	F	F	F
100	101	F	F	F	F	F	F	F	F	F	F	F	F
120	121	F	F	F	F	F	F	F	F	F	F	F	
150	151	F	F	F	F	F	F	F	F	F	F	F	
180	181	F	F	F	F	F	F	F	F	F	F	F	
220	221	F	F	F	F	F	F	F	F	F	F	F	
270	271	F	F	F	F	F	F	F	F	F	F	F	
330	331	F	F	F	F	F	F	F	F	F	F	F	
390	391	F	F	F	F	F	F	F	F	F	F	F	
470	471	F	F	F	F	F	F	F	F	F	F	F	
560	561	F	F	F	F	F	F	F	F	F	F	F	
680	681	F	F	F	F	F	F	F	F	F	F	F	
820	821	F	F	F	F	F	F	F	F	G	G	G	
1000	102	F	F	F	F	F	F	F	F	G	G	G	
1200	122	F	F	F	F	F	F	F	F	G	G	G	
1500	152	F	F	F	F	F	F	F	F	G	G	G	
1800	182	F	F	F	F	F	F	F	F	G	G	G	
2200	222	F	F	F	F	F	F	F	F	G	G	G	
2700	272	F	F	F	F	F	F	F	F	G	G	G	
3300	332	F	F	F	F	F	F	F	F	G	G	G	
3900	392	F	F	F	F	F	F	F	F	G	G		
4700	472	F	F	F	F	F	F	F	F	G	G		
5600	562	F	F	F	F	F	F	F	G	G	G		
6800	682	F	F	F	F	F	F	F	G	G	G		
8200	822	F	F	F	F	F	F	F	G	G	G		
10000	103	F	F	F	F	F	F	F	G	G	G		
12000	123	F	F	F	F	F	F	F	G				
15000	153	F	F	F	F	F	F	F					
18000	183	F	F	F	F	F	F	F					
22000	223	F	F	F	F	F	F	F					
27000	273	F	F	F	F	F	F	F					
33000	333	F	F	F	F	F	F	F					
39000	393	F	F	F	F	F	F	F					
47000	473	F	F	F	F	F	F	F					
56000	563	F	F	F	G	G	G	G					
68000	683	F	F	F	G	G	G	G					
82000	823	F	F	F	G	G	G	G					
100000	104	F	F	G	G	G							
120000	124	G	G	G									
150000	154												
180000	184												
220000	224												
270000	274												
330000	334												

Prosperity Dielectrics Co., Ltd.

7. CAPACITANCE RANGE

7-2. X7R

Dimension		0603					0805							
Cap.(pF)	Code	25V	50V	100V	200V	250V	25V	50V	100V	200V	250V	500V	630V	1000V
100	101	S	S	S	B	B	X	X	X	X	X	X	X	X
120	121	S	S	S	B	B	X	X	X	X	X	X	X	X
150	151	S	S	S	B	B	X	X	X	X	X	X	X	X
180	181	S	S	S	B	B	X	X	X	X	X	X	X	X
220	221	S	S	S	B	B	X	X	X	X	X	X	X	X
270	271	S	S	S	B	B	X	X	X	X	X	X	X	X
330	331	S	S	S	B	B	X	X	X	X	X	X	X	X
390	391	S	S	S	B	B	X	X	X	X	X	X	X	X
470	471	S	S	S	B	B	X	X	X	X	X	X	X	X
560	561	S	S	S	B	B	X	X	X	X	X	X	X	X
680	681	S	S	S	B	B	X	X	X	X	X	X	X	X
820	821	S	S	S	B	B	X	X	X	X	X	X	X	X
1000	102	S	S	S	B	B	X	X	X	X	X	X	X	X
1200	122	S	S	S	B	B	X	X	X	X	X	X	X	
1500	152	S	S	S	B	B	X	X	X	X	X	X	X	
1800	182	S	S	S	B	B	X	X	X	X	X	X	X	
2200	222	S	S	S	B	B	X	X	X	X	X	X	X	
2700	272	S	S	S	B	B	X	X	X	X	X	X	X	
3300	332	S	S	S	B	B	X	X	X	X	X	X	X	
3900	392	S	S	S	B	B	X	X	X	X	X	X	X	
4700	472	S	S	S	B	B	X	X	X	X	X	C	C	
5600	562	S	S	S	B	B	X	X	X	X	X	C	C	
6800	682	S	S	S	B	B	X	X	X	X	X	C	C	
8200	822	S	S	S	B	B	X	X	X	C	C	C	C	
10000	103	S	S	S	B	B	X	X	X	C	C	C	C	
12000	123	S	S	B			X	X	X	C	C	C	C	
15000	153	S	S	B			X	X	X	C	C	C	C	
18000	183	S	S	B			X	X	X	C	C	C	C	
22000	223	S	S	B			X	X	X	C	C	C	C	
27000	273	S	S	B			X	X	X	C	C	C	C	
33000	333	B	B	B			X	X	C	C	C			
39000	393	B	B	B			X	X	C					
47000	473	B	B	B			X	X	C					
56000	563	B	B	B			X	X	C					
68000	683	B	B	B			X	X	C					
82000	823	B	B				X	X	C					
100000	104	B	B				X	X	C					
120000	124						X	C	C					
150000	154						C	C	C					
180000	184						C	C	C					
220000	224						C	C	C					
270000	274						C	I	C					
330000	334						C	I	C					
390000	394						C	I	C					
470000	474						C	I	I					
560000	564						C	I						
680000	684						C	I						
820000	824						C	I						
1000000	105						C	I						

Prosperity Dielectrics Co., Ltd.

7. CAPACITANCE RANGE

7-2. X7R

Dimension		1206										1210									
Cap.(pF)	Code	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V
100	101	X	X	X	C	C	C	C	C	C	C										
120	121	X	X	X	C	C	C	C	C	C	C										
150	151	X	X	X	C	C	C	C	C	C	C										
180	181	X	X	X	C	C	C	C	C	C	C										
220	221	X	X	X	C	C	C	C	C	C	C	M	M	M	M	M	C	C	C	E	E
270	271	X	X	X	C	C	C	C	C	C	C	M	M	M	M	M	C	C	C	E	E
330	331	X	X	X	C	C	C	C	C	C	C	M	M	M	M	M	C	C	C	E	E
390	391	X	X	X	C	C	C	C	C	C	C	M	M	M	M	M	C	C	C	E	E
470	471	X	X	X	C	C	C	C	C	C	C	M	M	M	M	M	C	C	C	E	E
560	561	X	X	X	C	C	C	C	C	C	C	M	M	M	M	M	C	C	C	E	E
680	681	X	X	X	C	C	C	C	C	C	C	M	M	M	M	M	C	C	C	E	E
820	821	X	X	X	C	C	C	C	C	C	C	M	M	M	M	M	C	C	C	E	E
1000	102	X	X	X	C	C	C	C	C	C	C	M	M	M	M	M	C	C	C	E	E
1200	122	X	X	X	C	C	C	C	C	E	E	M	M	M	M	M	C	C	C	F	F
1500	152	X	X	X	C	C	C	C	C	E	E	M	M	M	M	M	C	C	C	F	F
1800	182	X	X	X	C	C	C	C	C	E	E	M	M	M	M	M	C	C	C	F	F
2200	222	X	X	X	C	C	C	C	C	E	E	M	M	M	M	M	C	C	C	F	F
2700	272	X	X	X	C	C	C	C	C	E	E	M	M	M	M	M	C	C	C	G	G
3300	332	X	X	X	C	C	C	C	C	E	E	M	M	M	M	M	C	C	C	G	G
3900	392	X	X	X	C	C	C	C	C	E	E	M	M	M	M	M	C	C	E	G	G
4700	472	X	X	X	C	C	C	C	C	E	E	M	M	M	M	M	C	C	E	G	G
5600	562	X	X	X	C	C	C	C	C			M	M	M	M	M	C	C	E	G	G
6800	682	X	X	X	C	C	C	C	C			M	M	M	M	M	C	C	E	G	G
8200	822	X	X	X	C	C	C	C	C			M	M	M	M	M	C	C	E	G	G
10000	103	X	X	X	C	C	C	C	C			M	M	M	M	M	C	C	E		
12000	123	X	X	X	C	C	C	C	C	E	E	M	M	M	M	M	C	C	E		
15000	153	X	X	X	C	C	C	C	E			M	M	M	M	M	C	C	E		
18000	183	X	X	X	C	C	C	C	E			M	M	M	M	M	C	C	E		
22000	223	X	X	X	C	C	E	E	E			M	M	M	M	M	C	C	E		
27000	273	X	X	X	C	C	E	E	E			M	M	M	M	M	E	E	E		
33000	333	X	X	X	E	E	E	E				M	M	M	M	M	E	E	E		
39000	393	X	X	X	E	E	E	E				M	M	M	M	M	E	E	F		
47000	473	X	X	X	E	E	E	E				M	M	M	C	C	E	E	G		
56000	563	X	X	X	E	E						M	M	M	C	C	E	E			
68000	683	X	X	X	E	E						M	M	M	E	E	F	F			
82000	823	X	X	C	E	E						M	M	M	E	E	G	G			
100000	104	X	X	C	E	E						M	M	M	E	E	G	G			
120000	124	X	X	C								M	M	M	E	E	G	G			
150000	154	M	M	E								M	M	C	G	G					
180000	184	M	M	E								M	M	C	G	G					
220000	224	M	M	E								M	M	C	G	G					
270000	274	M	C	E								M	M	E	G	G					
330000	334	M	C	E								M	C	E	G	G					
390000	394	J	P	E								M	C	E	G	G					
470000	474	J	P	E								M	C	G	G	G					
560000	564	J	P	P								C	C	G	G	G					
680000	684	J	P	P								C	C	F	G	G					
820000	824	J	P	P								C	C	F							
1000000	105	J	P	P								C	C	F							
1200000	125	P	P									C	G	G							
1500000	155	P	P									E	G	G							
1800000	185	P	P									G	G	G							
2200000	225	P	P									G	G	G							
2700000	275											G	G	G							
3300000	335											G	G	G							
3900000	395											G	G								
4700000	475											G	G								

Prosperity Dielectrics Co., Ltd.

7. CAPACITANCE RANGE(Con.)

7-2. X7R

Dimension		1808												1812											
Cap. (pF)	Code	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V	4000V	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V	4000V
150	151	C	C	C	C	C	C	C	C	C	C	C	F												
180	181	C	C	C	C	C	C	C	C	C	C	C	F												
220	221	C	C	C	C	C	C	C	C	C	C	C	F												
270	271	C	C	C	C	C	C	C	C	C	C	C	F	C	C	C	C	C	C	C	C	C	C	E	F
330	331	C	C	C	C	C	C	C	C	C	C	C	F	C	C	C	C	C	C	C	C	C	C	E	F
390	391	C	C	C	C	C	C	C	C	C	C	C	F	C	C	C	C	C	C	C	C	C	C	E	F
470	471	C	C	C	C	C	C	C	C	C	C	C	F	C	C	C	C	C	C	C	C	C	C	E	F
560	561	C	C	C	C	C	C	C	C	C	C	C	F	C	C	C	C	C	C	C	C	C	C	E	F
680	681	C	C	C	C	C	C	C	C	C	C	C	F	C	C	C	C	C	C	C	C	C	C	F	F
820	821	C	C	C	C	C	C	C	C	C	C	C	F	C	C	C	C	C	C	C	C	C	C	F	F
1000	102	C	C	C	C	C	C	C	C	C	C	C	F	C	C	C	C	C	C	C	C	C	C	F	F
1200	122	C	C	C	C	C	C	C	C	C	F	F	F	C	C	C	C	C	C	C	C	C	C	F	G
1500	152	C	C	C	C	C	C	C	C	C	F	F	F	C	C	C	C	C	C	C	C	C	C	F	G
1800	182	C	C	C	C	C	C	C	C	F	F	F		C	C	C	C	C	C	C	C	E	E	G	G
2200	222	C	C	C	C	C	C	C	C	F	F	F		C	C	C	C	C	C	C	C	E	E	G	
2700	272	C	C	C	C	C	C	C	C	F	F	F		C	C	C	C	C	C	C	C	E	E	G	
3300	332	C	C	C	C	C	C	C	C	F	F	F		C	C	C	C	C	C	C	C	F	F	G	
3900	392	C	C	C	C	C	C	C	C	F	F	F		C	C	C	C	C	C	C	C	F	F	G	
4700	472	C	C	C	C	C	C	C	C	F	F	K		C	C	C	C	C	C	C	C	F	F	G	
5600	562	C	C	C	C	C	F	F	F	F	F			C	C	C	C	C	C	C	C	G	G		
6800	682	C	C	C	C	C	F	F	F	F	F			C	C	C	C	C	C	C	C	G	G		
8200	822	C	C	C	C	C	F	F	F	F				C	C	C	C	C	C	C	C	G	G		
10000	103	C	C	C	C	C	F	F	F					C	C	C	C	C	C	C	E	G	G		
12000	123	E	E	E	E	E	F	F	F					C	C	C	C	C	C	C	F				
15000	153	E	E	E	E	E	F	F	F					C	C	C	C	C	C	C	F				
18000	183	E	E	E	E	E	F	F	F					C	C	C	C	C	C	C	G				
22000	223	E	E	E	E	E	F	F	F					C	C	C	C	C	C	C	G				
27000	273	E	E	E	E	E	F	F	F					C	C	C	C	C	C	C	G				
33000	333	E	E	E	E	E	F	F	F					C	C	C	C	C	C	C	G				
39000	393	E	E	E	E	E	F	F	F					C	C	C	C	C	C	C	G				
47000	473	E	E	E	E	E	F	F	F					C	C	C	C	C	C	C	G				
56000	563	E	E	E	E	E	F	F	F					C	C	C	C	C	F	F	G				
68000	683	E	E	E	E	E	F	F	F					C	C	C	C	C	F	F	G				
82000	823	E	E	E	E	E	F	F						C	C	C	C	C	F	F	G				
100000	104	E	E	E	E	E								C	C	E	C	C	F	F	G				
120000	124	E	E	E										C	C	E	C	C	G	G					
150000	154	E	E	E										C	C	E	F	F	G	G					
180000	184													C	C	E	F	F	G	G					
220000	224													C	C	E	F	F	G	G					
270000	274													C	C	E	F	F	G						
330000	334													C	C	E	F	F	G						
390000	394													C	C	E	F	F	G						
470000	474													C	C	E	F	F	G						
560000	564													C	C	F	G	G							
680000	684													C	F	F	G	G							
820000	824													C	F	F	G	G							
1000000	105													C	F	F	G	G							
1200000	125													C	F	F									
1500000	155													C	F	F									
1800000	185													E	F	F									
2200000	225													E	F	G									
2700000	275													F	F	G									
3300000	335													F	F	G									
3900000	395													F	F	G									
4700000	475													G	G	G									
5600000	565													G	G										
6800000	685													G	G										
8200000	825													G	G										
10000000	106													G	G										

Prosperity Dielectrics Co., Ltd.

7. CAPACITANCE RANGE

7-2. X7R

Dimension		1825											
Cap.(pF)	Code	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V	4000V
270	271												F
330	331												F
390	391												F
470	471												F
560	561												F
680	681												F
820	821												F
1000	102	F	F	F	F	F	F	F	F	F	F	F	F
1200	122	F	F	F	F	F	F	F	F	F	F	F	G
1500	152	F	F	F	F	F	F	F	F	F	F	F	G
1800	182	F	F	F	F	F	F	F	F	F	F	F	G
2200	222	F	F	F	F	F	F	F	F	F	F	F	
2700	272	F	F	F	F	F	F	F	F	F	F	F	
3300	332	F	F	F	F	F	F	F	F	F	F	F	
3900	392	F	F	F	F	F	F	F	F	F	F	F	
4700	472	F	F	F	F	F	F	F	F	F	F	F	
5600	562	F	F	F	F	F	F	F	F	F	F	F	G
6800	682	F	F	F	F	F	F	F	F	F	F	G	
8200	822	F	F	F	F	F	F	F	F	F	F	G	
10000	103	F	F	F	F	F	F	F	F	F	F	G	
12000	123	F	F	F	F	F	F	F	F	G	G	H	
15000	153	F	F	F	F	F	F	F	F	G	G	H	
18000	183	F	F	F	F	F	F	F	F	G	G	H	
22000	223	F	F	F	F	F	F	F	F	G	G		
27000	273	F	F	F	F	F	F	F	F	H	H		
33000	333	F	F	F	F	F	F	F	F	H	H		
39000	393	F	F	F	F	F	F	F	F	H	H		
47000	473	F	F	F	F	F	F	F	F	H	H		
56000	563	F	F	F	F	F	F	F	F				
68000	683	F	F	F	F	F	F	F	F				
82000	823	F	F	F	F	F	F	F	G				
100000	104	F	F	F	F	F	F	F	G				
120000	124	F	F	F	F	F	F	F					
150000	154	F	F	F	F	F	F	F					
180000	184	F	F	F	F	F	F	F					
220000	224	F	F	F	F	F	F	F					
270000	274	F	F	F	F	F	F	F					
330000	334	F	F	F	F	F	F	F					
390000	394	F	F	F	F	F	F	F					
470000	474	F	F	F	F	F	F	F					
560000	564	F	F	F	F	F	G	G					
680000	684	F	F	F	F	F							
820000	824	F	F	F	F	F							
1000000	105	F	F	F	F	F							
1200000	125	F	F	F									
1500000	155	F	F	F									
1800000	185	F	F	F									
2200000	225	F	F	F									
2700000	275	F	F	F									
3300000	335	F	F	F									
3900000	395	F	F	F									
4700000	475	F	F	G									
5600000	565	G	G	G									
6800000	685	G	G	G									
8200000	825	G	G	G									
10000000	106	G	G	G									

7. CAPACITANCE RANGE(Con.)

7-2. X7R

Dimension	Code	2220												2225											
		25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V	4000V	25V	50V	100V	200V	250V	500V	630V	1000V	1500V	2000V	3000V	4000V
100	101																								
120	121																								
150	151																								
180	181																								
220	221																								
270	271											F												F	
330	331											F												F	
390	391											F												F	
470	471											F												F	
560	561											F												F	
680	681											F												F	
820	821											F												F	
1000	102	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
1200	122	F	F	F	F	F	F	F	F	F	F	F	G	F	F	F	F	F	F	F	F	F	F	G	
1500	152	F	F	F	F	F	F	F	F	F	F	F	G	F	F	F	F	F	F	F	F	F	F	G	
1800	182	F	F	F	F	F	F	F	F	F	F	F	G	F	F	F	F	F	F	F	F	F	F	G	
2200	222	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
2700	272	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
3300	332	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
3900	392	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
4700	472	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
5600	562	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	G	
6800	682	F	F	F	F	F	F	F	F	F	F	G	F	F	F	F	F	F	F	F	F	F	F	G	
8200	822	F	F	F	F	F	F	F	G	G	G	F	F	F	F	F	F	F	F	F	F	F	F	G	
10000	103	F	F	F	F	F	F	F	G	G	G	F	F	F	F	F	F	F	F	F	F	F	F	G	
12000	123	F	F	F	F	F	F	F	G	G	H	F	F	F	F	F	F	F	F	F	G	G	G	G	
15000	153	F	F	F	F	F	F	F	G	G	H	F	F	F	F	F	F	F	F	F	G	G	G	G	
18000	183	F	F	F	F	F	F	F	H	H	H	F	F	F	F	F	F	F	F	F	G	G	H	H	
22000	223	F	F	F	F	F	F	F	H	H	H	F	F	F	F	F	F	F	F	F	G	G	G	G	
27000	273	F	F	F	F	F	F	F	H	H	H	F	F	F	F	F	F	F	F	F	G	G	G	G	
33000	333	F	F	F	F	F	F	F	H	H	H	F	F	F	F	F	F	F	F	F	G	G	G	G	
39000	393	F	F	F	F	F	F	F	H	H	H	F	F	F	F	F	F	F	F	F	G	H	H	H	
47000	473	F	F	F	F	F	F	F	H	H	H	F	F	F	F	F	F	F	F	F	G	H	H	H	
56000	563	F	F	F	F	F	F	F	F	H	H	F	F	F	F	F	F	F	F	F	G	H	H	H	
68000	683	F	F	F	F	F	F	F	G	G	G	F	F	F	F	F	F	F	F	F	G	H	H	H	
82000	823	F	F	F	F	F	F	F	G	G	G	F	F	F	F	F	F	F	F	F	G	H	H	H	
100000	104	F	F	F	F	F	F	F	G	G	G	F	F	F	F	F	F	F	F	G	G	H	H	H	
120000	124	F	F	F	F	F	F	F	G	G	G	F	F	F	F	F	F	F	F	H	H	H	H	H	
150000	154	F	F	F	F	F	F	F	H	H	H	F	F	F	F	F	F	F	F	H	H	H	H	H	
180000	184	F	F	F	F	F	F	F	H	H	H	F	F	F	F	F	F	F	F	H	H	H	H	H	
220000	224	F	F	F	F	F	F	F	H	H	H	F	F	F	F	F	F	F	F	H	H	H	H	H	
270000	274	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
330000	334	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
390000	394	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
470000	474	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F	
560000	564	F	F	F	F	F	G	G	G	G	G	F	F	F	F	F	F	F	F	F	F	F	F	F	
680000	684	F	F	F	F	F	G	G	G	G	G	F	F	F	F	F	F	F	F	F	F	F	F	F	
820000	824	F	F	F	F	F	H	H	H	H	H	F	F	F	F	F	G	G	G	G	H	H	H	H	
1000000	105	F	F	F	F	F	H	H	H	H	H	F	F	F	F	F	H	H	H	H	H	H	H	H	
1200000	125	F	F	F	G	G	G	G	G	G	G	F	F	F	G	G	H	H	H	H	H	H	H	H	
1500000	155	F	F	F	G	G	G	G	G	G	G	F	F	F	G	G	H	H	H	H	H	H	H	H	
1800000	185	F	F	F	G	G	G	G	G	G	G	F	F	F	G	G	H	H	H	H	H	H	H	H	
2200000	225	F	F	F	G	G	G	G	G	G	G	F	F	F	G	G	H	H	H	H	H	H	H	H	
2700000	275	F	F	F	G	G	G	G	G	G	G	F	F	F	G	G	H	H	H	H	H	H	H	H	
3300000	335	F	F	F	G	G	G	G	G	G	G	F	F	F	G	G	H	H	H	H	H	H	H	H	
3900000	395	F	F	F	G	G	G	G	G	G	G	F	F	F	G	G	H	H	H	H	H	H	H	H	
4700000	475	F	F	F	G	G	G	G	G	G	G	F	F	F	G	G	H	H	H	H	H	H	H	H	
5600000	565	F	F	F	G	G	G	G	G	G	G	F	F	F	G	G	H	H	H	H	H	H	H	H	
6800000	685	F	F	F	G	G	G	G	G	G	G	F	F	F	G	G	H	H	H	H	H	H	H	H	
8200000	825	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	
10000000	106	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	
12000000	126	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	
15000000	156	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	
18000000	186	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	
22000000	226	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	H	



8. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																			
1.	Visual and Dimensions	---	* No remarkable defect. * Dimensions to confirm to individual specification sheet.																			
2.	Capacitance		* Shall not exceed the limits given in the detailed spec.																			
3.	Q/ D.F. (Tangent of loss angle)	* Class I : (C0G) Cap.≤1000pF, 1.0±0.2Vrms, 1MHz±10%. Cap.>1000pF, 1.0±0.2Vrms, 1KHz±10%.	<table border="1"> <thead> <tr> <th>Dielectric</th> <th>Rated Vol.(V)</th> <th>Q/D.F.</th> <th>Remark</th> </tr> </thead> <tbody> <tr> <td rowspan="2">Class I</td> <td rowspan="2">All</td> <td>Q≥1000</td> <td>Cap.≥30pF</td> </tr> <tr> <td>Q≥400+20C</td> <td>Cap.<30pF</td> </tr> <tr> <td rowspan="3">Class II</td> <td rowspan="2">25V</td> <td>D.F.≤3.5%</td> <td></td> </tr> <tr> <td>D.F.≤2.5%</td> <td></td> </tr> <tr> <td>≥50</td> <td>D.F.≤3.0%</td> <td>0603≥0.047μF, 0805≥0.18μF, 1206≥0.47μF</td> </tr> </tbody> </table>	Dielectric	Rated Vol.(V)	Q/D.F.	Remark	Class I	All	Q≥1000	Cap.≥30pF	Q≥400+20C	Cap.<30pF	Class II	25V	D.F.≤3.5%		D.F.≤2.5%		≥50	D.F.≤3.0%	0603≥0.047μF, 0805≥0.18μF, 1206≥0.47μF
		Dielectric	Rated Vol.(V)	Q/D.F.	Remark																	
Class I	All	Q≥1000	Cap.≥30pF																			
		Q≥400+20C	Cap.<30pF																			
Class II	25V	D.F.≤3.5%																				
		D.F.≤2.5%																				
	≥50	D.F.≤3.0%	0603≥0.047μF, 0805≥0.18μF, 1206≥0.47μF																			
	* Class II : (X7R) 1.0±0.2Vrms, 1.0KHz±10% for Cap.≤10μF. 0.5±0.2Vrms, 120Hz±20% for Cap.>10μF.																					
4.	Temperature Coefficient (Temperature characteristic of capacitance)	* With no electrical load.																				
		<table border="1"> <thead> <tr> <th>T.C.</th> <th>Operating Temp.</th> </tr> </thead> <tbody> <tr> <td>C0G</td> <td>-55~125°C at 25°C</td> </tr> <tr> <td>X7R</td> <td>-55~125°C at 25°C</td> </tr> </tbody> </table>	T.C.	Operating Temp.	C0G	-55~125°C at 25°C	X7R	-55~125°C at 25°C	<table border="1"> <thead> <tr> <th>T.C.</th> <th>Capacitance Change</th> </tr> </thead> <tbody> <tr> <td>C0G</td> <td>Within ±30ppm/°C</td> </tr> <tr> <td>X7R</td> <td>Within ±15%</td> </tr> </tbody> </table>	T.C.	Capacitance Change	C0G	Within ±30ppm/°C	X7R	Within ±15%							
T.C.	Operating Temp.																					
C0G	-55~125°C at 25°C																					
X7R	-55~125°C at 25°C																					
T.C.	Capacitance Change																					
C0G	Within ±30ppm/°C																					
X7R	Within ±15%																					
5.	Insulation Resistance	<table border="1"> <thead> <tr> <th>Rated Vol.(V)</th> <th>Apply Voltage</th> <th>Test Condition</th> </tr> </thead> <tbody> <tr> <td>=100</td> <td>1 times of U_R</td> <td>Max. 120 sec.</td> </tr> <tr> <td>200≤V≤500</td> <td>1 times of U_R</td> <td>60 sec.</td> </tr> <tr> <td>>500</td> <td>500Vdc</td> <td>60 sec.</td> </tr> </tbody> </table>	Rated Vol.(V)	Apply Voltage	Test Condition	=100	1 times of U _R	Max. 120 sec.	200≤V≤500	1 times of U _R	60 sec.	>500	500Vdc	60 sec.	<table border="1"> <thead> <tr> <th>Dielectric</th> <th>Requirements</th> </tr> </thead> <tbody> <tr> <td>Class I</td> <td>≥10GΩ or RxC≥ 500Ω-F, whichever is smaller</td> </tr> <tr> <td>Class II</td> <td>≥10GΩ or RxC≥ 100Ω-F, whichever is smaller</td> </tr> </tbody> </table>	Dielectric	Requirements	Class I	≥10GΩ or RxC≥ 500Ω-F, whichever is smaller	Class II	≥10GΩ or RxC≥ 100Ω-F, whichever is smaller	
		Rated Vol.(V)	Apply Voltage	Test Condition																		
=100	1 times of U _R	Max. 120 sec.																				
200≤V≤500	1 times of U _R	60 sec.																				
>500	500Vdc	60 sec.																				
Dielectric	Requirements																					
Class I	≥10GΩ or RxC≥ 500Ω-F, whichever is smaller																					
Class II	≥10GΩ or RxC≥ 100Ω-F, whichever is smaller																					
6.	Solderability	* Solder temperature : 235±5°C for (0603~1210). * Solder temperature : 245±5°C for (1808~2225). * Dipping time : 2±0.5 sec.	* 75% min. coverage of all metalized area.																			
7.	Dielectric Strength (Voltage proof)	<table border="1"> <thead> <tr> <th>Rated Vol.(V)</th> <th>Condition</th> </tr> </thead> <tbody> <tr> <td>≤100</td> <td>2.0 times of U_R</td> </tr> <tr> <td>200<V≤500</td> <td>1.5 times of U_R</td> </tr> <tr> <td>=630</td> <td>1.2 times of U_R</td> </tr> <tr> <td>1000≤V≤5000V</td> <td>1.0 times of U_R</td> </tr> </tbody> </table>	Rated Vol.(V)	Condition	≤100	2.0 times of U _R	200<V≤500	1.5 times of U _R	=630	1.2 times of U _R	1000≤V≤5000V	1.0 times of U _R	* No evidence of damage or flashover during test.									
		Rated Vol.(V)	Condition																			
≤100	2.0 times of U _R																					
200<V≤500	1.5 times of U _R																					
=630	1.2 times of U _R																					
1000≤V≤5000V	1.0 times of U _R																					
* Duration : 1 to 5 sec. * Charge and discharge current less than 50mA.																						
8.	Resistance to Soldering Heat	* Solder temperature : 260±5°C. * Dipping time : 10±1 sec. * Preheating : 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder. * Before initial measurement (Class II only) : Perform 150 +0/-10°C for 1 hr and then set for 48±4 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).	* No remarkable damage.																			
		<table border="1"> <thead> <tr> <th>Dielectric</th> <th>Cap. Change</th> <th>Q/D.F. & I.R.</th> </tr> </thead> <tbody> <tr> <td>Class I (C0G)</td> <td>Within ±2.5% or ±0.25pF, whichever is larger</td> <td rowspan="2">To meet Initial requirement</td> </tr> <tr> <td>Class II (X7R)</td> <td>Within ±7.5%</td> </tr> </tbody> </table>	Dielectric	Cap. Change	Q/D.F. & I.R.	Class I (C0G)	Within ±2.5% or ±0.25pF, whichever is larger	To meet Initial requirement	Class II (X7R)	Within ±7.5%	* 25% max. leaching on each edge.											
Dielectric	Cap. Change	Q/D.F. & I.R.																				
Class I (C0G)	Within ±2.5% or ±0.25pF, whichever is larger	To meet Initial requirement																				
Class II (X7R)	Within ±7.5%																					

8. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																										
9.	Temperature Cycle Rapid (change of temperature)	* Conduct the five cycles according to the temperatures and time. <table border="1"> <thead> <tr> <th>Step</th> <th>Temp.(°C)</th> <th>Time(min.)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Min. operating emp. +0/-3</td> <td>30±3</td> </tr> <tr> <td>2</td> <td>Room temp.</td> <td>2~3</td> </tr> <tr> <td>3</td> <td>Max. operating temp. +3/-0</td> <td>30±3</td> </tr> <tr> <td>4</td> <td>Room temp.</td> <td>2~3</td> </tr> </tbody> </table>	Step	Temp.(°C)	Time(min.)	1	Min. operating emp. +0/-3	30±3	2	Room temp.	2~3	3	Max. operating temp. +3/-0	30±3	4	Room temp.	2~3	* No remarkable damage. <table border="1"> <thead> <tr> <th>Dielectric</th> <th>I.R.</th> <th>Cap. Change</th> <th>Q/D.F.</th> </tr> </thead> <tbody> <tr> <td>Class I (C0G)</td> <td rowspan="2">To meet Initial requirement</td> <td>Within ±2.5% or ±0.25pF, whichever is larger</td> <td>Q≥100% of initial requirement</td> </tr> <tr> <td>Class II (X7R)</td> <td>Within ±7.5%</td> <td>D.F.≤150% of initial requirement</td> </tr> </tbody> </table>	Dielectric	I.R.	Cap. Change	Q/D.F.	Class I (C0G)	To meet Initial requirement	Within ±2.5% or ±0.25pF, whichever is larger	Q≥100% of initial requirement	Class II (X7R)	Within ±7.5%	D.F.≤150% of initial requirement
		Step	Temp.(°C)	Time(min.)																									
1	Min. operating emp. +0/-3	30±3																											
2	Room temp.	2~3																											
3	Max. operating temp. +3/-0	30±3																											
4	Room temp.	2~3																											
Dielectric	I.R.	Cap. Change	Q/D.F.																										
Class I (C0G)	To meet Initial requirement	Within ±2.5% or ±0.25pF, whichever is larger	Q≥100% of initial requirement																										
Class II (X7R)		Within ±7.5%	D.F.≤150% of initial requirement																										
		* Before initial measurement (Class II only) : Perform 150 +0/-10°C for 1 hr and then set for 48±4 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).																											
10.	Humidity (Damp Heat) Steady State	* Test temp. : 40±2°C. * Humidity : 90~95%RH. * Test time : 500 +24/-0 hrs. * Measurement to be made after keeping at room temp. for 24±2 hrs. (Class I) or 48±4 hrs. (Class II).	* No remarkable damage. <table border="1"> <thead> <tr> <th>Dielectric</th> <th>I.R.</th> <th>Cap. Change</th> <th>Q/D.F.</th> </tr> </thead> <tbody> <tr> <td>Class I (C0G)</td> <td rowspan="2">≥1GΩ or RxC≥50Ω-F, whichever is smaller</td> <td>Within ±5.0% or ±0.5pF, whichever is larger</td> <td>Cap.≥30pF Q≥350 10pF≤Cap.<30pF Q≥275+2.5C</td> </tr> <tr> <td>Class II (X7R)</td> <td>Within ±12.5%</td> <td>Cap.<10pF Q≥200+10C D.F.≤200% of initial requirement</td> </tr> </tbody> </table>	Dielectric	I.R.	Cap. Change	Q/D.F.	Class I (C0G)	≥1GΩ or RxC≥50Ω-F, whichever is smaller	Within ±5.0% or ±0.5pF, whichever is larger	Cap.≥30pF Q≥350 10pF≤Cap.<30pF Q≥275+2.5C	Class II (X7R)	Within ±12.5%	Cap.<10pF Q≥200+10C D.F.≤200% of initial requirement															
		Dielectric		I.R.	Cap. Change	Q/D.F.																							
Class I (C0G)	≥1GΩ or RxC≥50Ω-F, whichever is smaller	Within ±5.0% or ±0.5pF, whichever is larger	Cap.≥30pF Q≥350 10pF≤Cap.<30pF Q≥275+2.5C																										
Class II (X7R)		Within ±12.5%	Cap.<10pF Q≥200+10C D.F.≤200% of initial requirement																										
		* Test temp. : 85±2°C. * Humidity : 85% RH. * Test time : 500 +24/-0 hrs. * To apply voltage : Rated voltage (100Vdc max.). * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).																											
11.	Humidity (Damp Heat) Load	* Test temp. : 85±2°C. * Humidity : 85% RH. * Test time : 500 +24/-0 hrs. * To apply voltage : Rated voltage (100Vdc max.). * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).	* No remarkable damage. <table border="1"> <thead> <tr> <th>Dielectric</th> <th>I.R.</th> <th>Cap. Change</th> <th>Q/D.F.</th> </tr> </thead> <tbody> <tr> <td>Class I (C0G)</td> <td rowspan="2">≥1GΩ or RxC≥50Ω-F, whichever is smaller</td> <td>Within ±7.5% or ±0.75pF, whichever is larger</td> <td>Cap.≥30pF Q≥350 10pF≤Cap.<30pF Q≥275+2.5C</td> </tr> <tr> <td>Class II (X7R)</td> <td>Within ±12.5%</td> <td>Cap.<10pF Q≥200+10C D.F.≤200% of initial requirement</td> </tr> </tbody> </table>	Dielectric	I.R.	Cap. Change	Q/D.F.	Class I (C0G)	≥1GΩ or RxC≥50Ω-F, whichever is smaller	Within ±7.5% or ±0.75pF, whichever is larger	Cap.≥30pF Q≥350 10pF≤Cap.<30pF Q≥275+2.5C	Class II (X7R)	Within ±12.5%	Cap.<10pF Q≥200+10C D.F.≤200% of initial requirement															
		Dielectric		I.R.	Cap. Change	Q/D.F.																							
Class I (C0G)	≥1GΩ or RxC≥50Ω-F, whichever is smaller	Within ±7.5% or ±0.75pF, whichever is larger	Cap.≥30pF Q≥350 10pF≤Cap.<30pF Q≥275+2.5C																										
Class II (X7R)		Within ±12.5%	Cap.<10pF Q≥200+10C D.F.≤200% of initial requirement																										
		* Test temp. : 125±3°C. <table border="1"> <thead> <tr> <th>Dielectric</th> <th>Rated Vol.(V)</th> <th>Apply Voltage</th> </tr> </thead> <tbody> <tr> <td rowspan="3">C0G X7R</td> <td>≤100</td> <td>2.0 times of UR</td> </tr> <tr> <td>250≤V≤500</td> <td>1.5 times of UR</td> </tr> <tr> <td>=630</td> <td>1.2 times of UR</td> </tr> </tbody> </table>	Dielectric	Rated Vol.(V)	Apply Voltage	C0G X7R	≤100	2.0 times of UR	250≤V≤500	1.5 times of UR	=630	1.2 times of UR																	
Dielectric	Rated Vol.(V)	Apply Voltage																											
C0G X7R	≤100	2.0 times of UR																											
	250≤V≤500	1.5 times of UR																											
	=630	1.2 times of UR																											
12.	High Temperature Load (Endurance)	* Exception item (X7R only) : <table border="1"> <thead> <tr> <th>Rated Vol.(V)</th> <th>Size</th> <th>Cap. Range</th> <th>Apply Voltage</th> </tr> </thead> <tbody> <tr> <td rowspan="7">100</td> <td>0805</td> <td>≥124</td> <td rowspan="7">2.0 times of UR</td> </tr> <tr> <td>1206</td> <td rowspan="6">≥105</td> </tr> <tr> <td>1210</td> </tr> <tr> <td>1808</td> </tr> <tr> <td>1812</td> </tr> <tr> <td>1825</td> </tr> <tr> <td>2220 2225</td> </tr> </tbody> </table>	Rated Vol.(V)	Size	Cap. Range	Apply Voltage	100	0805	≥124	2.0 times of UR	1206	≥105	1210	1808	1812	1825	2220 2225	* No remarkable damage. <table border="1"> <thead> <tr> <th>Dielectric</th> <th>I.R.</th> <th>Cap. Change</th> <th>Q/D.F.</th> </tr> </thead> <tbody> <tr> <td>Class I (C0G)</td> <td rowspan="2">≥1GΩ or RxC≥50Ω-F, whichever is smaller</td> <td>Within ±3.0% or ±0.3pF, whichever is larger</td> <td>Cap.≥30pF Q≥350 10pF≤Cap.<30pF Q≥275+2.5C</td> </tr> <tr> <td>Class II (X7R)</td> <td>Within ±12.5%</td> <td>Cap.<10pF Q≥200+10C D.F.≤200% of initial requirement</td> </tr> </tbody> </table>	Dielectric	I.R.	Cap. Change	Q/D.F.	Class I (C0G)	≥1GΩ or RxC≥50Ω-F, whichever is smaller	Within ±3.0% or ±0.3pF, whichever is larger	Cap.≥30pF Q≥350 10pF≤Cap.<30pF Q≥275+2.5C	Class II (X7R)	Within ±12.5%	Cap.<10pF Q≥200+10C D.F.≤200% of initial requirement
		Rated Vol.(V)	Size	Cap. Range	Apply Voltage																								
100	0805	≥124	2.0 times of UR																										
	1206	≥105																											
	1210																												
	1808																												
	1812																												
	1825																												
	2220 2225																												
Dielectric	I.R.	Cap. Change	Q/D.F.																										
Class I (C0G)	≥1GΩ or RxC≥50Ω-F, whichever is smaller	Within ±3.0% or ±0.3pF, whichever is larger	Cap.≥30pF Q≥350 10pF≤Cap.<30pF Q≥275+2.5C																										
Class II (X7R)		Within ±12.5%	Cap.<10pF Q≥200+10C D.F.≤200% of initial requirement																										
		* Test time : 1000 +24/-0 hrs. * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).																											

8. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements						
13	Resistance to Flexure of Substrate (Substrate bending test)	<p>* The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1mm per second until the deflection becomes 1mm.</p>  <p>Unit:mm</p>	<p>* No remarkable damage.</p> <table border="1"> <thead> <tr> <th>Dielectric</th> <th>Cap. Change</th> </tr> </thead> <tbody> <tr> <td>Class I (C0G)</td> <td>Within ±3.0% or ±0.3pF, whichever is larger</td> </tr> <tr> <td>Class II (X7R)</td> <td>Within ±12.5%</td> </tr> </tbody> </table> <p>(This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test)</p>	Dielectric	Cap. Change	Class I (C0G)	Within ±3.0% or ±0.3pF, whichever is larger	Class II (X7R)	Within ±12.5%
Dielectric	Cap. Change								
Class I (C0G)	Within ±3.0% or ±0.3pF, whichever is larger								
Class II (X7R)	Within ±12.5%								
14.	Adhesive Strength of Termination (Robustness of termination)	<p>* Capacitors mounted on a substrate. A force of 5N(≤0603) or 10N(>0603) applied perpendicular to the place of substrate and parallel the line joining the center of terminations for 10±1 second.</p>  <p>Capacitor, P.C. Board, Pressurizing force</p>	<p>* No remarkable damage or removal of the terminations.</p>						
15.	Vibration Resistance	<p>* Vibration frequency : 10~55 Hz/min. * Total amplitude : 1.5mm. * Test time : 6 hrs. (Two hrs each in three mutually perpendicular directions)</p>	<p>* No remarkable damage. * Cap. change and Q/D.F. : To meet initial spec.</p>						

9. PACKAGE DIMENSION AND QUANTITY

Size	Thickness (mm)	Paper tape		Plastic tape	
		7" reel	13" reel	7" reel	13" reel
0201(0603)	0.30±0.03	15k	70k	-	-
	0.30±0.05	15k	-	-	-
	0.30±0.09	15k	-	-	-
0402(1005)	0.50±0.05	10k	50k	-	-
	0.50 +0.02/-0.05	10k	50k	-	-
0603(1608)	0.50±0.20	10k	-	-	-
	0.50±0.10	4k	-	-	-
	0.80±0.07	4k	15k	-	-
0805(2012)	0.80 +0.15/-0.10	4k	15k	-	-
	0.50±0.10	4k	15k	-	-
	0.60±0.10	4k	15k	-	-
1206(3216)	0.80±0.10	4k	15k	-	-
	0.85±0.10	4k	15k	-	-
	0.95±0.10	-	-	3k	10k
	1.15±0.15	-	-	3k	10k
	1.25±0.10	-	-	3k	10k
	1.60±0.20	-	-	2k	10k
1210(3225)	1.60 +0.30/-0.10	-	-	2k	9k
	0.85±0.10	-	-	3k	10k
	0.95±0.10	-	-	3k	10k
	1.25±0.10	-	-	3k	10k
	1.60±0.20	-	-	2k	-
	2.00±0.20	-	-	1k	6k
1808(4520)	2.50±0.30	-	-	1k	6k
	1.25±0.10	-	-	2k	10k
	1.60±0.20	-	-	2k	8k
1812(4532)	2.00±0.20	-	-	1k	6k
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	3k
	2.80±0.30	-	-	0.5k	-
1825(4563)	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	-
2220(5750)	2.80±0.30	-	-	0.5k	-
	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	-
2225(5763)	2.80±0.30	-	-	0.5k	-
	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
2225(5763)	2.50±0.30	-	-	0.5k	-
	2.80±0.30	-	-	0.5k	-
	2.80±0.30	-	-	0.5k	-

Unit : pcs

9. PACKAGE DIMENSION AND QUANTITY

9.1. EMBOSSED TAPE DIMENSIONS




Fig. 9.1 The dimension of paper tape




Fig. 9.2 The dimension of plastic tape

Size	0603		0805		1206		
Chip Thickness	0.80±0.07	0.80 +0.15/-0.10	0.80±0.10	1.25±0.10 1.25±0.20	0.80±0.10	0.95±0.10 1.25±0.10	1.60±0.20 1.60+0.3/-0/1
A ₀	1.00 +0.05/-0.10	1.02 +0.05/-0.10	1.50±0.10	<1.65	2.00±0.10	<2.00	<2.00
B ₀	1.80±0.10	1.80±0.10	2.30±0.10	<2.40	3.50±0.10	<3.60	<3.70
T	0.95±0.05	0.97±0.05	0.95±0.05	0.23±0.05	0.95±0.05	0.23±0.05	0.23±0.05
K ₀	-	-	-	<2.50	-	<2.50	<2.50
W	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10
P ₀	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
10xP ₀	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20
P ₁	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
P ₂	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D ₀	1.55±0.05	1.55±0.05	1.55±0.05	1.50+0.10/-0	1.55±0.05	1.50+0.10/-0	1.50+0.10/-0
D ₁	-	-	-	1.00±0.10	-	1.00±0.10	1.00±0.10
E	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05
Unit :	mm	mm	mm	mm	mm	mm	mm

Size	1210		1808		1812	
Chip Thickness	0.95±0.10 1.25±0.10 1.60±0.20	2.50±0.30	1.25±0.10 1.60±0.20	2.00±0.20	1.25±0.10 1.60±0.20 2.00±0.20	2.50±0.30
A ₀	<3.05	<3.10	<2.50	<2.50	<3.90	<3.90
B ₀	<3.80	<4.00	<5.30	<5.30	<5.30	<5.30
T	0.23±0.05	0.23±0.05	0.25±0.05	0.25±0.05	0.25±0.05	0.25±0.05
K ₀	<2.50	<3.50	<2.50	<2.50	<2.50	<3.00
W	8.00±0.10	8.00±0.10	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20
P ₀	4.00±0.100	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
10xP ₀	40.00±0.20	40.0±0.10	40.0±0.20	40.0±0.20	40.00±0.20	40.00±0.20
P ₁	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	8.00±0.10	8.00±0.10
P ₂	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D ₀	1.50+0.10/-0	1.50+0.10/-0	1.50+0.10/-0	1.50+0.10/-0	1.50+0.10/-0	1.50+0.10/-0
D ₁	1.00±0.10	1.00±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10
E	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	3.50±0.05	3.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05
Unit :	mm	mm	mm	mm	mm	mm

9. PACKAGE DIMENSION AND QUANTITY

Size	1825		2220		2225	
Chip Thickness	1.60±0.20 2.00±0.20	2.50±0.30	1.40±0.15 1.60±0.20 2.00±0.20	2.50±0.30	1.60±0.20 2.00±0.20	2.50±0.30
A ₀	<6.80	<6.80	<5.80	<5.80	<6.80	<6.80
B ₀	<5.30	<5.30	<6.50	<6.50	<6.50	<6.50
T	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10
K ₀	<2.50	<3.10	<2.50	<3.10	<2.50	<3.10
W	12.00±0.20	12.00±0.20	12.00±0.20	12.00±0.20	12.00±0.20	12.00±0.20
P ₀	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
10xP ₀	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20
P ₁	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10
P ₂	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D ₀	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0
D ₁	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10
E	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05
Unit :	mm	mm	mm	mm	mm	mm

9.2. REEL DIMENSIONS

Size	0402, 0603, 0805, 1206, 1210			1808, 1812, 1825, 2220, 2225
Reel size	7"	7"	13"	7"
C	13.0 +0.5/-0.2	13.0 +0.5/-0.2	13.0 +0.7/-0.3	13.0 +0.5/-0.2
W ₁	8.4 +1.5/-0	12.4 +2.0/-0	8.4 +2.0/-0	12.4 +2.0/-0
A	178.0 ±0.10	178.0 ±0.10	330.0 ±1.0	178.0 ±0.10
N	60.0 +1.0/-0	80.0 ±1.0	100 ±1.0	60.0 +1.0/-0




Fig. 9.3 The dimension of reel

10. APPLICATION NOTES

STORAGE

To prevent the damage of solderability of terminations, the following storage conditions are recommended :
 Indoors under 5 ~ 40°C and 20% ~ 70% RH.

No harmful gases containing sulfuric acid, ammonia, hydrogen sulfide or chlorine.

Packaging should not be opened until the capacitors are required for use. If opened, the pack should be re-sealed as soon as is practicable. Taped product should be stored out of direct sunlight, which might promote deterioration in tape or adhesion performance. The product is recommended to be used within 12 months after shipment and checked the solderability before use.

HANDLING

Chip capacitors are dense, hard, brittle, and abrasive materials. They are liable to suffer mechanical damage, in the form of cracks or chips. Chip Capacitors should be handled with care to avoid contamination or damage. To use vacuum or plastic tweezers to pick up or plastic tweezers is recommended for manual placement. Tape and reeled packages are suitable for automatic pick and placement machine.


PREHEAT

In order to minimize the risk of thermal shock during soldering, a carefully controlled preheat is required. The rate of preheat should not exceed 3°C per second.

SOLDERING

Use middy activated rosin RA and RMA fluxes do not use activated flux. The amount of solder in each solder joint should be controlled to prevent the damage of chip capacitors caused by the stress between solder, chips, and substrate.


a.) Hand soldering :




- * Soldering iron tip diameter ≤ 1.0 mm and wattage max. 20W.
- * The Capacitors shall be pre-heated and that the temperature gradient between the devices and the tip of the soldering iron.
- * The required amount of solder shall be melted on the soldering tip.
- * The tip of iron should not contact the ceramic body directly.
- * The Capacitors shall be cooled gradually at room temperature after soldering.
- * Forced air cooling is not allowed.

10. APPLICATION NOTES

b.) Reflow soldering :



c.) Wave soldering :



Soldering conditions :

Class I :

Size Inch (mm)	Temper. Char.	Capacitance	Condition	
			Wave	Reflow
≤0402 (1005)	All Class I	All	X	O
0603 (1608)	All Class I	All	O	O
0805 (2012)	All Class I	All	O	O
1206 (3216)	All Class I	All	O	O
≥1210 (3225)	All Class I	All	X	O

10. APPLICATION NOTES

Soldering conditions :
 Class II :

Size Inch (mm)	Temper. Cher.	Capacitance	Condition	
			Wave	Reflow
≤0402 (1005)	All Class II	All	X	O
0603 (1608)	All Class II	Cap. <2.2μF	O	O
		Cap. ≥2.2μF	X	O
0805 (2012)	All Class II	Cap. <4.7μF	O	O
		Cap. ≥4.7μF	X	O
1206 (3216)	All Class II	Cap. <4.7μF	O	O
		Cap. ≥4.7μF	X	O
≥1210 (3225)	All Class II	All	X	O

Soldering height :

The solder climbing minimum height is suggesting to 25% of chip thickness or 500um whichever is less.
 (Reference from IPC-610E)

The diagram illustrates a cross-section of a chip on a substrate. The chip is shown in yellow and grey. A vertical double-headed arrow on the left indicates the 'Chip Thickness'. A vertical double-headed arrow on the right indicates the 'Soldering Height', which is the height of the solder joint between the chip and the substrate.

COOLING

After soldering, cool the chips and the substrate gradually to room temperature. Natural cooling in air is recommended to minimize stress in the solder joint.

CLEANING

All flux residues must be removed by using suitable electronic-grade vapor-cleaning solvents to eliminate contamination that could cause electrolytic surface corrosion. Good results can be obtained by using ultrasonic cleaning of the solvent. The choice of the proper system is depends upon many factors such as component mix, flux, and solder paste and assembly method. The ability of the cleaning system to remove flux residues and contamination from under the chips is very important.